



Categories	Components	Calcium carbonate content (wt.%)	Flow rate (190 Degree Celsius/2.16 kg) (g/10 min)	Bulk density (g/cm3)	Moisture (wt.%)
EFPE 1001	LLDPE, CaCO3, Dispersion agent, Processing aid	80	0.1	1.24	<0.08
EFPE 1002	LLDPE, CaCO3, Dispersion agent, Processing aid, TiO2	80	0.1	1.3	<0.08
EFPE 1010	LLDPE, CaCO3, Dispersion agent, Processing aid	75	0.98	1.13	<0.08
EFPE 1015	LLDPE, CaCO3, Dispersion agent, Processing aid	70	1.5	1.02	<0.08